

WPO 39636

General Purpose Granular


AMERICAN COLLOID COMPANY
 Industrial Chemical Division

Revised 1/85

VOLCLAY GPG 30

General Description: Granular sodium bentonite with an average particle size ranging between 20 and 70 mesh.

Functional Use: Multipurpose product noted for rapid dispersion in water. Employed in a wide variety of industrial applications. Volclay GPG-30 is commonly used by domestic contractors for remedial waterproofing.

Purity: Hydrous aluminum silicate comprised principally of the clay mineral montmorillonite. Montmorillonite content 90% minimum. Contains small portions of feldspar, biotite, selenite, etc.

Chemical Composition: Typical Analysis (moisture free)

SiO ₂	63.02%
Al ₂ O ₃	21.08%
Fe ₂ O ₃	3.25%
FeO	0.35%
MgO	2.67%
Na ₂ O	2.57%
CaO	0.65%
H ₂ O	5.64%
Trace Elements	0.72%

Chemical Formula: A tri-layer expanding mineral structure of approximately:
 (Al, Fe_{1.67}, Mg_{0.33}) Si₄O₁₀ (OH)₂ Na+Ca⁺⁺_{0.33}

Moisture Content: Maximum 12% as shipped

Dry Particle Size: Maximum 1% retained on 16 mesh
 Maximum 35% retained on 20 mesh
 Maximum 3.5% passing 70 mesh
 Maximum 1% passing 200 mesh

Wet Particle Size: Minimum 94% passing 200 mesh (74 microns)
 Minimum 92% passing 325 mesh (44 microns)

pH: 5% suspension 8.0 to 10.5

Viscosity: 6.25% solids - 8-30 cps

Free Swell: Minimum 24 milliliters per ² gram of clay

Packaging: 100-pound or 50-pound multi-wall paper bags, or bulk.

F.O.B.: 1500 W. State Street, Belle Fourche, SD
 Wilmington Heights, Illinois 60004-1434 • (708) 392-4600

The information and data contained herein are believed to be accurate and reliable. American Colloid Company makes no warranty of any kind and accepts no responsibility for the results obtained through application of this information.

SWCF - A: 1.1.4.3: REFS

Information Only